QC ABSTRACT

NAME OF WORK: Construction of Rooms and other Civil Works at Ambedkar Bhavana (Balance Portion) in Mallasandra Colony Ward No 13 Shettyhalli Sub Division

SL NO	Item Of Work	Name of Test	Frequency of Test/Quantity	Executed Quantity	Number of Tests Required	Number of Tests Conducted
		Materials				
1	Cement	Fineness by dry sieving	One Test		1	1
		Finess by Air permeablity method	One Test		1	1
		Density	One Test		1	1
		Standard Consistency	One Test		1	1
		Initial Setting time	One Test		1	1
		Final Setting time	One Test		1	1
		Soundness (Le Chatelier's Method)	One Test		1	1
		Compressive Strength	One Test		1	1
2	Coarse aggregate(40 mm down size)	SIEVE ANALYSIS	One Test		1	1
		Flakiness Index	One Test		1	1
		Elongation Index	One Test		1	1
		Specific Gravity	One Test		1	1
		Bulk Density(Loose)	One Test		1	1
		Bulk Density(Compacted)	One Test		1	1
		Water Absorption	One Test		1	1
3	Coarse aggregate(20 mm down size)	SIEVE ANALYSIS	One Test		1	1
		Flakiness Index	One Test		1	1
		Elongation Index	One Test		1	1
		Specific Gravity	One Test		1	1
		Bulk Density(Loose)	One Test		1	1
		Bulk Density(Compacted)	One Test		1	1
		Water Absorption	One Test		1	1
		Aggregate crushing Value	One Test		1	1
		Aggregate Impact Value	One Test		1	1
4	Fine aggregate	SIEVE ANALYSIS	One Test		1	1
		Water Absorption	One Test		1	1
		Specific Gravity	One Test		1	1
		Material finer than 75 micron	One Test		1	1
5	Steel	Bend test	One Test		1	1
		Tensile Test	One Test		1	1
		Yield Test	One Test		1	1
		ReBend test	One Test		1	1
6	Block(400*150*200)	BLOCK DENSITY	One Test		1	1
		WATER ABSORPTION	One Test		1	1
		DIMENSION ANALYSIS	One Test		1	1
		COMPRESSIVE STRENGTH	One Test		1	1
7	Precast (100mm)	Core Compressive Strength	One Test		1	1
		Corrected Cylinder Compressive Strength	One Test		1	1
		Equivalent Cube Compressive Strength	One Test		1	1

ಸಹಾಯಕ ಕಾರ್ಯಪಾಲಕ ಅಭಿಯಂತರರು
ಶೆಟ್ಟಿಹಳ್ಳಿ ಉಪವಿಭಾಗ, ದಾಸರಹಳ್ಳಿ ವಲಯ
ಬೃಹತ್ ಬೆಂಗಳೂರು ಮಹಾನಗರ ಪಾಲಿಕೆ
ಎಸ್.ಎಲ್.ವಿ ರಸ್ತೆ, ರವೀಂದ್ರನಗರ, ಬೆಂಗಳೂರು.

Scanned with CamScanner

8	Precast (250mm)	Core Compressive Strength	One Test		1	1
		Corrected Cylinder Compressive Strength	One Test		1	1
		Equivalent Cube Compressive Strength	One Test		1	1
9	PCC(M15)	Compressive Strength(7days and 28days)	2 set /6-15 cum	10.14	4	4
10	RCC(M20)	Compressive Strength(7days and 28days)	2 set /6-15 cum	10.43	4	4
11	RCC (M20)	Compressive Strength(7days and 28days)	2 set /6-15 cum	13.68	4	4
12	Column Concrete (M25)	Compressive Strength(7days and 28days)	2 set /6-15 cum	6.74	4	4
13	Lintel Concrete (M25)	Compressive Strength(7days and 28days)	1 set /1-5 cum	2.79	2	2
14	Staircase Concrete (M25)	Compressive Strength(7days and 28days)	1 set /1-5 cum	1.81	2	2
15	FF Roof Concrete (M25)	Compressive Strength(7days and 28days)	4 set /31-50 cum	37.21	8	8
16	Head Room Roof Concrete (M25)	Compressive Strength(7days and 28days)	1 set /1-5 cum	3.9	2	2
17	CERAMIC TILES	MEASUREMENTS OF LENGTH, WIDTH AND THICKNESS	One Test		1	1
		MODULUS OF RUPTURE AND BREAKING STRENGTH	One Test		1	1
18	Premix Carpet	SIEVE ANALYSIS	One Test		1	1
		Flakiness Index	One Test		1	1
		Elongation Index	One Test		1	1
		Specific Gravity	One Test		1	1
		Water Absorption	One Test		1	1
		Marshal Stability	One Test		1	1
		Marshal flow	One Test		1	1
		Percent air Voids	One Test		1	1
		Percent Voids in mineral Aggregate	One Test		1	1
		Percent Voids filled with Bitumen	One Test		1	1
		Density	One Test		1	1
		Stripping Value	One Test		1	1
		Aggregate Impact Value	One Test		1	1
19	Mortar Sand	Water Absorption	One Test		1	1
		Specific Gravity	One Test		1	1
		Material finer than 75 micron	One Test		1	1
		Compacted Bulk Density	One Test		1	1
		Loose Bulk Density	One Test		1	1
		SIEVE ANALYSIS	One Test		1	1
20	Plaster Sand	Water Absorption	One Test		1	1
		Specific Gravity	One Test		1	1
		Material finer than 75 micron	One Test		1	1
		SIEVE ANALYSIS	One Test		1	1

Scanned with CamScanner

Format No. CP/TF/01

TEST REPORT OF PHYSICAL PROPERTIES OF CEMENT - 53 Grade

Lab ID	:	CP-2020-05-11-15 **Date: 10-02-20**
Customer	:	Assistant Executive Engineer, Shettyhalli Sub Division, BBMP, Bangalore.
Address	:	Shettyhalli Sub Division, BBMP, Bangalore.
Project Name	:	Construction of Concrete Retaining Wall and other Civil Works to Mallasandra Colony School in Ward No 13 Shettyhalli Sub Division
Agency	:	M/S Technical Manager (West), Karnataka Rural Infrastructure Development Limited , No.280,59th Cross, 17th C Main Road , 3rd Y Block Rajaji Nagara, Bangaluru-560010
Customer's Reference	:	EE/DD/W.O/533/2019-20
Source of Sample	:	Sample supplied by Agency
Sample Condition	:	Satisfactory
Date of Receipt	:	07-02-20
Sample Type	:	Birla Super 53grade
Reference to BIS codes	:	IS 12269 : 2013, 53 Grade Ordinary Portland cement Specification , IS 4031 (Part 1,2 3,4,5, 6,11):1988 IS 4031 Part 1 DETERMINATION OF FINENESS BY DRY SIEVING, Clause 4.4 IS 4031 Part 2, Determination of Fineness by Blaine Air Permeability Method, Clause 5 IS 4031 Part 3, Determination of Soundness, Clause 5,Clause 6 IS 4031 Part 4, Determination of Consistency of Standard Cement Paste, Clause 5 IS 4031 Part 5, Determination of Initial & Final Setting Time, Clause 5 IS 4031 Part 11,DETERMINATION OF DENSITY , Clause 6
Date of test	:	08-02-20
Environmental Conditions during test	:	Temperature: 26°C Humidity: 72%

Sl.No.	Physical properties	Results	Requirement as per IS 12269: 2013
1	Fineness by dry sieving (%)	1.54	–
2	Finess by Air permeablity method (m^2/kg,Min)	298.2	225m^2/kg, Min
3	Density (gm/cc)	3.12	–
4	Standard Consistency (%)	29.0%	Not specified
5	Initial Setting time	160 minutes	Not less than 30 minutes
6	Final Setting time	255 minutes	Not more than 600 minutes
7	Soundness (Le Chatelier's Method)	2mm	Not more than 10 mm

Note:

The results pertain to the samples received and tested.

All information furnished by the Customer/Representative

Any correction in the report will make this report invalid

This report without prior written approval should not be reproduced or published in full or part.

Samples will be disposed after 90 days from the date of issue of test certificate

CIVIL Pro Sig Date BANGALORE

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

ಸಹಾಯಕ ಕಾರ್ಯಪಾಲಕ ಅಭಿಯಂತರರು
ಶೆಟ್ಟಿಹಳ್ಳಿ ಉಪವಿಭಾಗ, ದಾಸರಹಳ್ಳಿ ವಲಯ
ಬೃಹತ್ ಬೆಂಗಳೂರು ಮಹಾನಗರ ಪಾಲಿಕೆ
ಎಸ್.ಎಂ. ರಸ್ತೆ, ರವೀಂದ್ರನಗರ, ಬೆಂಗಳೂರು.

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

HIGHWAY & BUILDING MATERIALS TESTING LABORATORY | STRUCTURAL| GEO TECHNICAL| PROJECT MANAGEMENT| SURVEYING SERVICES|

Scanned with CamScanner

Format No: CP/TF/01

TEST REPORT OF PHYSICAL PROPERTIES OF CEMENT - 53 Grade

Lab ID	:	CP-2020-05-11-15 **Date: 07-03-20**
Customer	:	Assistant Executive Engineer, Shettyhalli Sub Division, BBMP, Bangalore.
Address	:	Shettyhalli Sub Division, BBMP, Bangalore.
Project Name	:	Construction of Concrete Retaining Wall and other Civil Works to Mallasandra Colony School in Ward No 13 Shettyhalli Sub Division
Agency	:	M/S Technical Manager (West), Karnataka Rural Infrastructure Development Limited , No.280,59th Cross, 17th C Main Road , 3rd Y Block Rajaji Nagara, Bangalura-560010
Customer's Refereace	:	EE/DD/W.O/533/2019-20
Source of Sample	:	Sample supplied by Agency
Sample Condition	:	Satisfactory
Date of Receipt	:	07-02-20
Sample Type	:	Birla Super 53grade
Reference to BIS codes	:	IS 12269 : 2013, 53 Grade Ordinary Portland cement Specification , IS 4031 Part 4, Determination of Consistency of Standard Cement Paste, Clause 5 IS 4031 Part 6, Determination of Compressive Strength, Clause 6
Date of test	:	08-02-20
Environmental Conditions during test	:	Temperature: 26°C Humidity: 72%

Compressive Strength

Sl.No.	Physical properties	Results	Requirement as per IS 12269: 2013
1	3 Days	28.5N/mm^2	Not less than 27 N/mm^2
2	7 Days	38.5N/mm^2	Not less than 37 N/mm^2
3	28 Days	59.0N/mm^2	Not less than 53 N/mm^2

Note:
The results pertain to the samples received and tested.
All information furnished by the Customer Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

CIVIL Pro

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

ಸಹಾಯಕ ಕಾರ್ಯಪಾಲಕ ಅಭಿಯಂತರರು
ಶೆಟ್ಟಿಹಳ್ಳಿ ಉಪವಿಭಾಗ, ದಾಸರಹಳ್ಳಿ ವಲಯ
ಬೃಹತ್ ಬೆಂಗಳೂರು ಮಹಾನಗರ ಪಾಲಿಕೆ
ಎಸ್.ಎಂ. ರಸ್ತೆ, ರವೀಂದ್ರನಗರ, ಯಶವಂತಪುರ

End of Report

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

Scanned with CamScanner

Format No: CP/TF/01

TEST REPORT ON COARSE AGGREGATES

Lab ID : CP-2020-05-11-15

Date: 10-02-20

Customer : Assistant Executive Engineer, Shettyhalli Sub Division, BBMP, Bangalore.

Address : Shettyhalli Sub Division, BBMP, Bangalore.

Project Name : Construction of Concrete Retaining Wall and other Civil Works to Mallasandra Colony School in Ward No 13 Shettyhalli Sub Division

Agency : M/S Technical Manager (West), Karnataka Rural Infrastructure Development Limited , No.280,59th Cross, 17th C Main Road , 3rd Y Block Rajaji Nagara, Bangaluru-560010

Customer's Reference : EE/DD/W.O/533/2019-20

Source of Sample : Sample supplied by Agency

Sample condition : Satisfactory

Date of Receipt : 07-02-20

Sample Type : 40mm down size coarse aggregate

Reference to BIS codes : IS: 383:2016 (Specification for Coarse and fine Aggregates)
IS: 2386 :1963(Part - 1,3,4) RA2011
IS 2386 Part 1: Particle Size and Shape
IS 2386 Part 3: Specific gravity, Density, Voids,Water Absorption
IS 2386 Part 4: Mechanical Properties

Date of test : 07-02-20

SIEVE ANALYSIS (PARTICLE SIZE DISTRIBUTION) OF 40MM DOWN COARSE AGGREGATE:

Total weight taken : **15000** **grams**

Sample No.	Sieve No.	Weight Retained in gms	Cumulative Weight Retained in gms	% Cumulative Weight Retained	% Passing	Required as per IS 383:2016
1	80 mm	0	0	0.0	100	100
2	40 mm	187	187	1.2	98.8	90-100
3	20 mm	7276	7463	49.8	50.2	30-70
4	10 mm	4074	11537	76.9	23.1	10-35
5	4.75 mm	3000	14537	96.9	3.1	0-5
6	Pan	463	15000	100.0	0	—

ಸಹಾಯಕ ಕಾರ್ಯಪಾಲಕ ಅಭಿಯಂತರರು

Scanned with CamScanner

Format No: CP/TF/01

TEST REPORT ON COARSE AGGREGATES

Lab ID : CP-2020-05-11-15 **Date:** 10-02-20

PHYSICAL PROPERTIES

Sl.no	Tests	Result	Requirements as per IS:383-2016
1	Flakiness Index(%)	12.4	Combined Flakiness & Elongation Index Shall not Exceed 40% for Uncrushed & Crushed Aggregate
2	Elongation Index(%)	11.8	
3	Specific Gravity	2.68	–
4	Bulk Density(Loose) (Kg/l)	1.53	–
5	Bulk Density(Compacted) (Kg/l)	1.57	–
6	Water Absorption(%)	0.23	–

Note:
The results pertain to the samples received and tested.
All information furnished by the Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 30 days from the date of issue of test certificate

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

Scanned with CamScanner

Format No: CP/TF/01

TEST REPORT ON COARSE AGGREGATES

Lab ID	:	CP-2020-05-11-15 **Date: 10-02-20**
Customer	:	Assistant Executive Engineer, Shettyhalli Sub Division, BBMP, Bangalore.
Address	:	Shettyhalli Sub Division, BBMP, Bangalore.
Project Name	:	Construction of Concrete Retaining Wall and other Civil Works to Mallasandra Colony School in Ward No 13 Shettyhalli Sub Division
Agency	:	M/S Technical Manager (West), Karnataka Rural Infrastructure Development Limited , No.280,59th Cross, 17th C Main Road , 3rd Y Block Rajaji Nagara, Bangaluru-560010
Customer Reference	:	EE/DD/W.O/533/2019-20
Source of Sample	:	Sample supplied by Agency
Sample Condition	:	Satisfactory
Date of Receipt	:	07-02-20
Sample Type/ Size	:	20mm down size coarse aggregate
Reference to BIS codes	:	IS: 383:2016 (Specification for Coarse and fine Aggregates) IS: 2386 :1963(Part - 1,3,4) RA2011 IS 2386 Part 1: Particle Size and Shape IS 2386 Part 3: Specific gravity, Density, Voids,Water Absorption IS 2386 Part 4: Mechanical Properties
Date of test	:	07-02-20

SIEVE ANALYSIS (PARTICLE SIZE DISTRIBUTION) OF 20MM DOWN COARSE AGGREGATE:

Total weight taken : 5000 grams

Sample No.	Sieve No.	Weight Retained in gms	Cumulative Weight Retained in gms	% Cumulative Weight Retained	% Passing	Required as per IS 383:2016
1	40 mm	0	0	0	100	100
2	20 mm	236	236	4.7	95.3	90-100
3	10 mm	2629	2865	57.3	42.7	25-55
4	4.75 mm	1779	4644	92.9	7.1	0-10
5	Pan	356	5000	100	0	-

CIVIL PRO Sig Date BANGALORE

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

Scanned with CamScanner

Format No: CP/TF/01

TEST REPORT ON COARSE AGGREGATES

Lab ID : **CP-2020-05-11-15** **Date: 10-02-20**

PHYSICAL PROPERTIES

Sl.no	Tests	Result	Requirements as per IS:383-2016
1	Flakiness Index(%)	9.3	Combined Flakiness & Elongation Index Shall not Exceed 40% for Uncrushed & Crushed Aggregate
2	Elongation Index(%)	10.7	
3	Specific Gravity	2.67	–
4	Bulk Density(Loose) (Kg/l)	1.54	–
5	Bulk Density(Compacted) (Kg/l)	1.58	–
6	Water Absorption(%)	0.22	–
7	Aggregate crushing Value(%)	24.5	Max 30% for Aggregates to be used in concrete for wearing Surface, In case Aggregate Crushing Value Exceeds 30% then the test for ten percent fines should be conducted for Aggregates to be used in concrete other than for wearing Surface.
8	Aggregate Impact Value(%)	23.5	30% for Aggregates to be used in concrete for wearing Surface, 45% for Aggregates to be used in concrete other than for wearing Surface.

Note:

The results pertain to the samples received and tested.
All information furnished by the Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

CIVIL Pro Sig Date BANGALORE

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signature
Quality Manager

End of Report

ಸಹಾಯಕ ಕಾರ್ಯಪಾಲಕ ಅಭಿಯಂತರರು
ಪೀಣ್ಯ ಉಪವಿಭಾಗ, ದಾಸರಹಳ್ಳಿ ವಲಯ
ಬೃಹತ್ ಬೆಂಗಳೂರು ಮಹಾನಗರ ಪಾಲಿಕೆ
ಎಸ್.ಎಂ. ರಸ್ತೆ, ರವೀಂದ್ರನಗರ, ಬೆಂಗಳೂರು.

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

Scanned with CamScanner

Format No: CP/TF/01

TEST REPORT OF FINE AGGREGATE

Lab ID	:	CP-2020-02-11-15
Customer	:	Assistant Executive Engineer, Shettyhalli Sub Division, BBMP, Bangalore.
Address	:	Shettyhalli Sub Division, BBMP, Bangalore.
Project Name	:	Construction of Concrete Retaining Wall and other Civil Works to Mallasandra Colony School in Ward No 13 Shettyhalli Sub Division
Agency	:	M/S Technical Manager (West), Karnataka Rural Infrastructure Development Limited , No.280,59th Cross, 17th C Main Road , 3rd Y Block Rajaji Nagara, Bangalore-560010
Customer's Reference	:	EE/DD/W.O/533/2019-20
Source of Sample	:	Sample supplied by Agency
Sample Condition	:	Satisfactory
Date of Receipt	:	07-02-20
Sample Type	:	Fine Aggregate
Reference to BIS codes	:	IS 383 : 2016 (Specification for Coarse and fine Aggregates) IS: 2386 :1963(Part - 1, 3) RA2012 IS 2386 Part 1: Particle Size and Shape IS 2386 Part 3: Specific gravity, Density, Voids, Water Absorption
Date of test	:	07-02-20
Total weight taken	:	1000 grams

Date: 10-02-20

Sl.no	Sieve Size	Weight Retained (gms)	Cumulative Weight Retained (gms)	% Cumulative Weight Retained	% Passing	Requirement as per IS 383:2016			
						Grading Zone I	Grading Zone II	Grading Zone III	Grading Zone IV
1	10 mm	0	0	0.0	100.0	100	100	100	100
2	4.75 mm	27	27	2.7	97.3	90-100	90-100	90-100	95-100
3	2.36 mm	55	82	8.2	91.8	60-95	75-100	85-100	95-100
4	1.18 mm	239	321	32.1	67.9	30-70	55-90	75-100	90-100
5	600 micron	206	527	52.7	47.3	15-34	35-59	60-79	80-100
6	300 micron	205	732	73.2	26.8	5-20	8-30	12-40	15-50
7	150 micron	191	923	92.3	7.7	0-10	0-10	0-10	0-15
8	Pan	77	1000	100.0	0.0	—	—	—	—

Result : The tested Sample Conforms to Grading Zone II

CIVIL PRO BANGALORE

M. : 9972936326 | Tel : +91 80 23444801 | e : raghavan6630@yahoo.co.in, civilproexperts@gmail.com

Scanned with CamScanner

CIVIL PRO
AN ISO 9001 : 2008 COMPANY &NABL ACCREDITED LABORATORY AS PER ISO/IEC 17025:2005
4, 7TH MAIN MALLESWARAM, BANGALORE -3
Certificate No : TC-0548

TEST REPORT OF FINE AGGREGATE

Lab ID : **CP-2020-05-11-15** **Date: 10-02-20**

PHYSICAL PROPERTIES

SLno	Tests	Result	Requirements as per IS 383:2016
1	Water Absorption(%)	1.5	-
2	Specific Gravity	2.59	-
3	Material finer than 75 micron(%)	6.9	Uncrushed fine Aggregate Max 3%, Crushed Fine aggregate Max 15%, Mixed Fine aggregate Max 12%, Manufactured Fine aggregate Max 10%

Note:

The results pertain to the samples received and tested.
All information furnished by the Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

CIVIL Pro Sig Date BANGALORE

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

Scanned with CamScanner